

STANDARD BAKED ENAMEL / KYNAR® COLORS



STANDARD ANODIZED COLORS

Slight color variation may occur in color anodized production runs.





PRIME COAT

When field painting is required, Architectural Louvers applies a modified zinc chromate primer. *This is not recommended* and field cleaning must be done before painting.

BAKED ENAMEL

A high quality yet economical finish for both aluminum and galvanized louvers.

After louvers are chemically cleaned, a prime coat is applied followed by approximately 1.5 mils of polyurethane acrylic enamel.

KYNAR 500®

Superior finish for louvers. Excellent for color retention and resistance to chemicals, chalking, fading, and weather damage. Meets AAMA specifications 605.2.

Five year warranty available on aluminum louvers.

Kynar 500 is a registered trademark of Penwalt Corporation.

204 R1 CLEAR ANODIZE

Designated by the Aluminum Assocation as AA-M10-C22A31.

Provides a clear anodize coating of .4 to .7 mils which enhances the appearance of aluminum louvers and increases their resistance to weather damage.

215 R1 CLEAR ANODIZE

Designated by the Aluminum Association as AA-M10-C22A41. Provides a clear anodize coating of .7 mils minimum. Provides superior weather resistance and is recommended for corrosive atmosphere.

COLORED ANODIZE

Designated by the Aluminum Association as AA-M10-C22A42.

Offers excellent weather and corrosion protection on aluminum louvers along with the added advantage of color.

Slight color variation may occur in production runs.